



K-Resin® KR01

INEOS Styrolution - Styrene Butadiene Block Copolymer

Friday, January 24, 2025

General Information

Product Description

K-Resin® KR01 process very well in injection molding, providing good cycle times and design flexibility. Applications range from containers and packaging with living hinges to medical applications, toys, displays, overcaps and hangers. INEOS Styrolution has several grades of KResin ® SBC tailored for your injection molded needs.

FEATURES

- Excellent Clarity
- Good Stiffness
- Good Toughness
- High Surface Gloss
- Warpage Resistance

APPLICATIONS

- Display Housings
- Medical Devices
- Toys
- Molded Boxes

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Block Copolymer • Good Processability • Good Stiffness	• Good Toughness • High Clarity • High Gloss	• Warp Resistant
Uses	• Containers • Displays	• Housings • Medical Devices	• Medical/Healthcare Applications • Toys
Appearance	• Clear/Transparent		
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	1.01 g/cm ³	1.01 g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (200°C/5.0 kg)	8.0 cm ³ /10min	8.0 cm ³ /10min	ISO 1133
Molding Shrinkage	0.30 to 1.0 %	0.30 to 1.0 %	ISO 294-4
Water Absorption			ISO 62
Equilibrium, 73°F (23°C), 50% RH	0.070 %	0.070 %	

Copyright ©, 2025, Formerra, LLC. All the information in this literature is for general information purpose only. Formerra makes no representations, guarantees, or warranties of any kind with respect to the information contained in this literature, including its accuracy, completeness, reliability, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for pricing, property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Formerra makes no warranties or guarantees respecting suitability of either Formerra's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. FORMERRA MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature or any other provided literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner. Any action you take upon the information you find in this literature is strictly at your own risk. Formerra will not be liable for any losses and/or damages in connection with the use of this literature. By using this literature, you hereby consent to this disclaimer and agree to its terms.

K-Resin® KR01

INEOS Styrolution - Styrene Butadiene Block Copolymer

Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus	232000 psi	1600 MPa	ISO 527-1
Tensile Stress			
Yield, 73°F (23°C)	4790 psi	33.0 MPa	ISO 527-2/1/50
Break, 73°F (23°C)	3480 psi	24.0 MPa	ISO 527-2
Tensile Strain (Break, 73°F (23°C))	15 %	15 %	ISO 527-2/1/50
Flexural Modulus ²			ISO 178
73°F (23°C), 0.125 in (3.18 mm)	218000 psi	1500 MPa	
Flexural Stress ²			ISO 178
73°F (23°C), 0.125 in (3.18 mm)	6530 psi	45.0 MPa	
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	0.71 ft·lb/in ²	1.5 kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
73°F (23°C)	14 ft·lb/in ²	30 kJ/m ²	
Notched Izod Impact Strength (73°F (23°C))	1.4 ft·lb/in ²	3.0 kJ/m ²	ISO 180/A
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Shore Hardness (Shore D)	70	70	ISO 868
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load			
66 psi (0.45 MPa), Unannealed	172 °F	78.0 °C	ISO 75-2/B
264 psi (1.8 MPa), Unannealed	149 °F	65.0 °C	ISO 75-2/A
Vicat Softening Temperature			
--	149 °F	65.0 °C	ISO 306/B50
--	203 °F	95.0 °C	ISO 306/A120
Optical	Typical Value (English)	Typical Value (SI)	Test Method
Light Transmittance (550 nm)	92.0 %	92.0 %	ASTM D1003
Haze	< 1.00 %	< 1.00 %	ASTM D1003

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Processing (Melt) Temp	356 to 464 °F	180 to 240 °C
Mold Temperature	86 to 122 °F	30 to 50 °C

Notes

¹ Typical properties: these are not to be construed as specifications.

² 0.50 in/min (13 mm/min)

Copyright ©, 2025, Formerra, LLC. All the information in this literature is for general information purpose only. Formerra makes no representations, guarantees, or warranties of any kind with respect to the information contained in this literature, including its accuracy, completeness, reliability, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for pricing, property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Formerra makes no warranties or guarantees respecting suitability of either Formerra's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. FORMERRA MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature or any other provided literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner. Any action you take upon the information you find in this literature is strictly at your own risk. Formerra will not be liable for any losses and/or damages in connection with the use of this literature. By using this literature, you hereby consent to this disclaimer and agree to its terms.