



# Makrolon® 2458

## Covestro - Polycarbonates - Polycarbonate

Friday, January 24, 2025

### General Information

#### Product Description

MVR (300°C/1.2 kg) 19 cm<sup>3</sup>/10 min; medical devices; suitable for ETO and steam sterilization at 121°C; biocompatible according to many ISO 10993-1 test requirements; low viscosity; easy release; injection molding - melt temperature 280 - 320°C; available in transparent and opaque colors

#### General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Biocompatible • Ethylene Oxide Sterilizable	• Good Mold Release • Low Viscosity	• Steam Sterilizable
Uses	• Medical Devices • Medical/Healthcare Applications		
Agency Ratings	• ISO 10993-1		
RoHS Compliance	• RoHS Compliant		
Appearance	• Clear/Transparent	• Colors Available	
Processing Method	• Injection Molding		
ISO Shortname	• ISO 7391-PC,MR,(,,-)18-9		

### ASTM & ISO Properties <sup>1</sup>

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density (73°F (23°C))	1.20 g/cm <sup>3</sup>	1.20 g/cm <sup>3</sup>	ISO 1183
Apparent (Bulk) Density <sup>2</sup>	0.66 g/cm <sup>3</sup>	0.66 g/cm <sup>3</sup>	ISO 60
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	20 g/10 min	20 g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	19 cm <sup>3</sup> /10min	19 cm <sup>3</sup> /10min	ISO 1133
Molding Shrinkage			
Across Flow	0.50 to 0.70 %	0.50 to 0.70 %	ISO 2577
Flow	0.50 to 0.70 %	0.50 to 0.70 %	ISO 2577
Across Flow : 536°F (280°C), 0.0787 in (2.00 mm) <sup>3</sup>	0.70 %	0.70 %	ISO 294-4
Flow : 0.0787 in (2.00 mm) <sup>3</sup>	0.65 %	0.65 %	ISO 294-4
Water Absorption			
Saturation, 73°F (23°C)	0.30 %	0.30 %	ISO 62
Equilibrium, 73°F (23°C), 50% RH	0.12 %	0.12 %	
<b>Mechanical</b>			
Tensile Modulus (73°F (23°C))	348000 psi	2400 MPa	ISO 527-1/1
Tensile Stress			
Yield, 73°F (23°C)	9430 psi	65.0 MPa	ISO 527-2/50
Break, 73°F (23°C)	10200 psi	70.0 MPa	

Copyright ©, 2025, Formerra, LLC. All the information in this literature is for general information purpose only. Formerra makes no representations, guarantees, or warranties of any kind with respect to the information contained in this literature, including its accuracy, completeness, reliability, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for pricing, property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Formerra makes no warranties or guarantees respecting suitability of either Formerra's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. FORMERRA MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature or any other provided literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner. Any action you take upon the information you find in this literature is strictly at your own risk. Formerra will not be liable for any losses and/or damages in connection with the use of this literature. By using this literature, you hereby consent to this disclaimer and agree to its terms.

# Makrolon® 2458

## Covestro - Polycarbonates - Polycarbonate

Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strain			ISO 527-2/50
Yield, 73°F (23°C)	6.1 %	6.1 %	
Break, 73°F (23°C)	130 %	130 %	
Nominal Tensile Strain at Break			ISO 527-2/50
73°F (23°C)	> 50 %	> 50 %	
Tensile Creep Modulus			ISO 899-1
1 hr	319000 psi	2200 MPa	
1000 hr	276000 psi	1900 MPa	
Flexural Modulus <sup>4</sup> (73°F (23°C))	341000 psi	2350 MPa	ISO 178
Flexural Stress <sup>4</sup>			ISO 178
73°F (23°C)	14100 psi	97.0 MPa	
3.5% Strain, 73°F (23°C)	10600 psi	73.0 MPa	
Flexural Strain at Flexural Strength <sup>5</sup>			ISO 178
73°F (23°C)	7.1 %	7.1 %	
<b>Impact</b>	<b>Typical Value (English)</b>	<b>Typical Value (SI)</b>	<b>Test Method</b>
Charpy Notched Impact Strength <sup>6</sup>			ISO 179/1eA
-22°F (-30°C), Complete Break	6.7 ft·lb/in <sup>2</sup>	14 kJ/m <sup>2</sup>	
73°F (23°C), Partial Break	31 ft·lb/in <sup>2</sup>	65 kJ/m <sup>2</sup>	
Charpy Unnotched Impact Strength			ISO 179/1eU
-76°F (-60°C)	No Break	No Break	
-22°F (-30°C)	No Break	No Break	
73°F (23°C)	No Break	No Break	
Notched Izod Impact Strength <sup>6</sup>			ISO 180/A
-22°F (-30°C), Complete Break	7.1 ft·lb/in <sup>2</sup>	15 kJ/m <sup>2</sup>	
73°F (23°C), Partial Break	31 ft·lb/in <sup>2</sup>	65 kJ/m <sup>2</sup>	
Multi-Axial Instrumented Impact Energy			ISO 6603-2
-22°F (-30°C)	47.9 ft·lb	65.0 J	
73°F (23°C)	40.6 ft·lb	55.0 J	
Multi-Axial Instrumented Impact Peak Force			ISO 6603-2
-22°F (-30°C)	1350 lbf	6000 N	
73°F (23°C)	1150 lbf	5100 N	
<b>Hardness</b>	<b>Typical Value (English)</b>	<b>Typical Value (SI)</b>	<b>Test Method</b>
Ball Indentation Hardness	16700 psi	115 MPa	ISO 2039-1

Copyright ©, 2025, Formerra, LLC. All the information in this literature is for general information purpose only. Formerra makes no representations, guarantees, or warranties of any kind with respect to the information contained in this literature, including its accuracy, completeness, reliability, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for pricing, property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Formerra makes no warranties or guarantees respecting suitability of either Formerra's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. FORMERRA MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature or any other provided literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner. Any action you take upon the information you find in this literature is strictly at your own risk. Formerra will not be liable for any losses and/or damages in connection with the use of this literature. By using this literature, you hereby consent to this disclaimer and agree to its terms.

# Makrolon® 2458

## Covestro - Polycarbonates - Polycarbonate

Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load			
66 psi (0.45 MPa), Unannealed	282 °F	139 °C	ISO 75-2/B
264 psi (1.8 MPa), Unannealed	257 °F	125 °C	ISO 75-2/A
Glass Transition Temperature <sup>7</sup>	295 °F	146 °C	ISO 11357-2
Vicat Softening Temperature			
--	295 °F	146 °C	ISO 306/B120
--	293 °F	145 °C	ISO 306/B50
Ball Pressure Test (280°F (138°C))	Pass	Pass	IEC 60695-10-2
CLTE			ISO 11359-2
Flow : 73 to 131°F (23 to 55°C)	3.6E-5 in/in/°F	6.5E-5 cm/cm/°C	
Transverse : 73 to 131°F (23 to 55°C)	3.6E-5 in/in/°F	6.5E-5 cm/cm/°C	
Thermal Conductivity <sup>8</sup> (73°F (23°C))	1.4 Btu·in/hr/ft <sup>2</sup> /°F	0.20 W/m/K	ISO 8302
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	1.0E+16 ohms	1.0E+16 ohms	IEC 60093
Volume Resistivity (73°F (23°C))	1.0E+16 ohms·cm	1.0E+16 ohms·cm	IEC 60093
Electric Strength			IEC 60243-1
73°F (23°C), 0.0394 in (1.00 mm)	860 V/mil	34 kV/mm	
Relative Permittivity			IEC 60250
73°F (23°C), 100 Hz	3.10	3.10	
73°F (23°C), 1 MHz	3.00	3.00	
Dissipation Factor			IEC 60250
73°F (23°C), 100 Hz	5.0E-4	5.0E-4	
73°F (23°C), 1 MHz	9.0E-3	9.0E-3	
Comparative Tracking Index (Solution A)	250 V	250 V	IEC 60112
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Oxygen Index <sup>9</sup>	28 %	28 %	ISO 4589-2
Flash Ignition Temperature	896 °F	480 °C	ASTM D1929
Self Ignition Temperature	1022 °F	550 °C	ASTM D1929
Optical	Typical Value (English)	Typical Value (SI)	Test Method
Refractive Index <sup>10</sup>	1.586	1.586	ISO 489
Light Transmittance			ISO 13468-2
39.37 mil (1000 µm)	89.0 %	89.0 %	
78.74 mil (2000 µm)	89.0 %	89.0 %	
118.1 mil (3000 µm)	88.0 %	88.0 %	
157.5 mil (4000 µm)	87.0 %	87.0 %	
Haze (118.1 mil (3000 µm))	< 0.800 %	< 0.800 %	ISO 14782

### Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature - Dry Air Dryer	248 °F	120 °C
Drying Time - Dry Air Dryer	2.0 to 3.0 hr	2.0 to 3.0 hr
Suggested Max Moisture	< 0.020 %	< 0.020 %
Suggested Shot Size	30 to 70 %	30 to 70 %
Rear Temperature	482 to 500 °F	250 to 260 °C

Copyright ©, 2025, Formerra, LLC. All the information in this literature is for general information purpose only. Formerra makes no representations, guarantees, or warranties of any kind with respect to the information contained in this literature, including its accuracy, completeness, reliability, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for pricing, property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Formerra makes no warranties or guarantees respecting suitability of either Formerra's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. FORMERRA MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature or any other provided literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner. Any action you take upon the information you find in this literature is strictly at your own risk. Formerra will not be liable for any losses and/or damages in connection with the use of this literature. By using this literature, you hereby consent to this disclaimer and agree to its terms.

# Makrolon® 2458

## Covestro - Polycarbonates - Polycarbonate

Injection	Typical Value (English)	Typical Value (SI)
Middle Temperature	518 to 536 °F	270 to 280 °C
Front Temperature	536 to 554 °F	280 to 290 °C
Nozzle Temperature	554 to 572 °F	290 to 300 °C
Processing (Melt) Temp	536 to 608 °F	280 to 320 °C
Mold Temperature	176 to 248 °F	80 to 120 °C
Back Pressure	725 to 2180 psi	5.00 to 15.0 MPa
Vent Depth	9.8E-4 to 3.0E-3 in	0.025 to 0.075 mm

### Injection Notes

Peripheral Screw Speed: 0.05 - 0.2 m/s  
 Hold Pressure (% of Injection Pressure): 50 - 75%  
 Standard Melt Temperature: 300°C

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> Pellets

<sup>3</sup> 60x60x2mm, 500 bar

<sup>4</sup> 0.079 in/min (2.0 mm/min)

<sup>5</sup> 2.0 mm/min

<sup>6</sup> 3 mm

<sup>7</sup> 10°C/min

<sup>8</sup> Across Flow

<sup>9</sup> Procedure A

<sup>10</sup> Method A

Copyright ©, 2025, Formerra, LLC. All the information in this literature is for general information purpose only. Formerra makes no representations, guarantees, or warranties of any kind with respect to the information contained in this literature, including its accuracy, completeness, reliability, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for pricing, property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Formerra makes no warranties or guarantees respecting suitability of either Formerra's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. FORMERRA MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature or any other provided literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner. Any action you take upon the information you find in this literature is strictly at your own risk. Formerra will not be liable for any losses and/or damages in connection with the use of this literature. By using this literature, you hereby consent to this disclaimer and agree to its terms.