



Versaflex™ OM 6240-1

Avient Corporation - Thermoplastic Elastomer

Thursday, February 6, 2025

General Information

Product Description

Versaflex™ OM 6240-1 is specifically designed to bond to a variety of standard and modified nylon materials, including those which are glass-filled, heat stabilized and/or impact modified.

- Exceptional Colorability
- Outstanding Adhesion in Two-Shot Molding Processes
- Soft, Rubbery Grip
- Very Easy to Process

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Good Adhesion	• Good Colorability	• Good Processability
Uses	• Consumer Applications • Flexible Grips	• Overmolding • Soft Touch Applications	
RoHS Compliance	• RoHS Compliant		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.09	1.09	ASTM D792
Molding Shrinkage - Flow	0.019 to 0.026 in/in	1.9 to 2.6 %	ASTM D955
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Stress ^{2, 3}			ASTM D412
100% Strain, 73°F (23°C)	150 psi	1.03 MPa	
300% Strain, 73°F (23°C)	243 psi	1.68 MPa	
Tensile Strength ^{2, 3} (Break, 73°F (23°C))	285 psi	1.97 MPa	ASTM D412
Tensile Elongation ^{2, 3} (Break, 73°F (23°C))	510 %	510 %	ASTM D412
Tear Strength	90.0 lbf/in	15.8 kN/m	ASTM D624
Compression Set (73°F (23°C), 22 hr)	22 %	22 %	ASTM D395B
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness			ASTM D2240
Shore A, 10 sec, 73°F (23°C)	43	43	

Copyright ©, 2025, Formerra, LLC. All the information in this literature is for general information purpose only. Formerra makes no representations, guarantees, or warranties of any kind with respect to the information contained in this literature, including its accuracy, completeness, reliability, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for pricing, property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Formerra makes no warranties or guarantees respecting suitability of either Formerra's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. FORMERRA MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature or any other provided literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner. Any action you take upon the information you find in this literature is strictly at your own risk. Formerra will not be liable for any losses and/or damages in connection with the use of this literature. By using this literature, you hereby consent to this disclaimer and agree to its terms.

Versaflex™ OM 6240-1

Avient Corporation - Thermoplastic Elastomer

Fill Analysis	Typical Value (English)	Typical Value (SI)	Test Method
Apparent Viscosity 392°F (200°C), 11200 sec ⁻¹	31.3 Pa·s	31.3 Pa·s	ASTM D3835

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Suggested Max Regrind	20 %	20 %
Rear Temperature	360 to 400 °F	182 to 204 °C
Middle Temperature	470 to 510 °F	243 to 266 °C
Front Temperature	480 to 520 °F	249 to 271 °C
Nozzle Temperature	490 to 530 °F	254 to 277 °C
Processing (Melt) Temp	480 to 520 °F	249 to 271 °C
Mold Temperature	55 to 85 °F	13 to 29 °C
Back Pressure	0.00 to 80.0 psi	0.00 to 0.552 MPa
Screw Speed	80 to 120 rpm	80 to 120 rpm

Injection Notes

Color concentrates with EVA or LDPE carriers are most suitable for coloring Versaflex™ OM 6240-1. Typical ratios are 50:1 to 25:1 - loading levels should be as low as possible to minimize the effect on adhesion. A high color match consistency can be obtained by the use of precolored compounds available from GLS. Polypropylene (PP) based color concentrates are not recommended because they can significantly affect adhesion of the TPE to the nylon. Concentrates based on PVC should not be used. The final determination of color concentrate suitability should be determined by customer trials.

Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polyethylene (PE) or polypropylene (PP).

Regrind levels up to 20% can be used with Versaflex™ OM 6240-1 with minimal property loss, provided that the regrind is free of contamination. To minimize losses during molding, the melt temperature should remain as low as possible. The final determination of regrind effectiveness should be determined by the customer.

Versaflex™ OM 6240-1 has good melt stability. Maximum residence times may vary, depending on the size of the barrel. Generally, the barrel should be emptied if it is idle for periods of 8 - 10 minutes or longer.

Drying is not Required

Injection Speed: 3 to 5 in/sec

1st Stage - Boost Pressure: 300 to 800 psi

2nd Stage - Hold Pressure: 0% of Boost

Hold Time (Thick Part): 0 to 4 sec

Hold Time (Thin Part): 0 to 3 sec

Notes

¹ Typical properties: these are not to be construed as specifications.

² Die C

³ 2 hr

Copyright ©, 2025, Formerra, LLC. All the information in this literature is for general information purpose only. Formerra makes no representations, guarantees, or warranties of any kind with respect to the information contained in this literature, including its accuracy, completeness, reliability, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for pricing, property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Formerra makes no warranties or guarantees respecting suitability of either Formerra's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. FORMERRA MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature or any other provided literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner. Any action you take upon the information you find in this literature is strictly at your own risk. Formerra will not be liable for any losses and/or damages in connection with the use of this literature. By using this literature, you hereby consent to this disclaimer and agree to its terms.