STEREOLITHOGRAPHY

ABS-LIKE TRANSLUCENT/CLEAR







STANDARD

NATURAL

Product Description

ABS-Like Translucent/Clear offers a unique combination of low moisture absorption and near-colorless transparency. Custom finishing is required to achieve functional clarity. Its tensile strength and elongation at break are among the highest of 3D-printed, thermoset material.

Applications

ABS-Like Translucent/Clear can be used for general-purpose applications but is ideal for flow-visualization models, microfluidics, and light pipes.



Key Product Benefits

- ► Functional clarity
- ▶ Water resistant

Tolerances

For well-designed parts, tolerances in the X/Y dimension of ±0.002 in. (0.05mm) for the first inch plus ±0.001 in./in., and Z-dimension tolerances of ±0.005 in. (0.127mm) for the first inch plus ±0.001 in./in. (0.001mm/mm), can typically be achieved. Note that tolerances may change depending on part geometry.

Properties

| Property | Test Method | Value |
|---|--------------------------------|--|
| Color | - | Translucent with Standard Finish / Clear with Custom Finish |
| Density in solid state* | @ 25 °C (77 °F) | 1.12 g/cm³ |
| Water absorption (20 °C, 50% relative humidity) | ASTM D570 | 0.35 ± 0.15% |
| E-module (x-y plane) | ASTM D638, test speed 10mm/min | 2,900 ± 400 MPa |
| Tensile strength (x-y plane) | ASTM D638, test speed 10mm/min | 55 ± 10 MPa |
| Elongation at break (x-y plane) | ASTM D638, test speed 10mm/min | 6 ± 3% |
| Heat deflection temperature @ 0.46 MPa* | ASTM D648 | 45.9 – 54.5 °C (115 – 130 °F) |
| Heat deflection temperature @ 1.82 MPa* | ASTM D648 | 49.0 – 49.7 °C (120 °F) |

* From supplier data sheet

